

Ratings

Voltage: 300 V
 Temperature: 80 °C

Conductor

Gauge: 26 AWG
 Material: tinned copper strands
 Strand size: Ø 0.16 mm
 Strand count: 7

Insulator

Material: PVC, 80 °C
 Color: black, white
 Nominal thickness: 0.23 mm
 Outer diameter: 1.10 mm



Outer jacket

Material: PVC, 80°C
 Color: gray
 Thickness: 0.76 mm
 Diameter: 3.8 ± 0.15 mm
 Durometer: 91 Shore A

Wire marking: E339579 AWM STYLE 2464 26AWG 80°C 300V VW-1 --- C AWM I A 80°C 300V FT1 LF TENSILITY HLE

Tests

Voltage test: 300 V
 Spark test: 3.0 kV
 Max resistance at 20 °C: 150 ohm/km
 Insulation tensile strength: 2.11 kgf/mm²
 Jacket tensile strength: 1.05 kgf/mm²
 After aging at 113 ± 2 °C for 7 days:
 Minimum tensile strength 70 % original
 Minimum elongation 65 % original
 Heat shock: 121 ± 1 °C /1 hour, no observed degradation
 Deformation: 121 ± 1 °C /1 hour, ≤ 50 %
 Cold bend: -10 ± 1 °C /1 hour, no observed cracking
 Flammability: VW-1
 Dielectric test: 2000 V ac for 1 minute without breakdown



REVISION	DATE	DESCRIPTION
A	06/30/2014	Initial release

PREPARED:	NOTES: RoHS and REACH compliant
VERIFIED:	Electrical test: no open, no short circuit, no intermittent
DIMENSIONS ARE IN MILLIMETERS	DESCRIPTION: Wire, 2C TS, 26 AWG, UL2464, 300V, 80C, 3.8 mm, VW-1, PVC, 91A, gray
TOLERANCES: X: ± 0.5 mm X.X: ± 0.3 mm X.XX: ± 0.05 mm	

TENSILITY

20802 Sockeye Place #130
 Bend, OR 97701 USA
 tel 541.323.3228 fax 541.323.4202
 800 877.670.7118 www.tensility.com

SIZE A	PART NUMBER 30-00364
SCALE: 10:1	WEIGHT:
SHEET 1 OF 1	